

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>D04H 1/64, D06M 15/19, 15/37, 15/59,</b> <b>15/693, D21H 17/20</b>	<b>A1</b>	<b>(11) International Publication Number: *      WO 98/32906</b> <b>(43) International Publication Date:              30 July 1998 (30.07.98)</b>
<b>(21) International Application Number:</b> PCT/EP97/00376 <b>(22) International Filing Date:</b> 28 January 1997 (28.01.97)  <b>(71) Applicant (for all designated States except MG):</b> CAMELOT SUPERABSORBENTS LIMITED [CA/CA]; #3 1411 - 25th Avenue N.E., Calgary, Alberta (CA).  <b>(71) Applicant (for MG only):</b> CAMELOT SUPERABSORBENTS B.V. [NL/NL]; Hengelosestraat 706, Postbus 545, NL-7500 AM Enschede (NL).  <b>(72) Inventors:</b> BOUMAN, Dirk; Groen Van Prinstererlaan 42, NL-7521 AZ Enschede (NL). SHALTRY, Michael, J.; 9925 Pallisers Terrace, Charlotte, NC 28120 (US).  <b>(74) Agent:</b> SMAGGASGALE, Gillian, Helen; Mathys & Squire, 100 Gray's Inn Road, London WC1X 8AL (GB).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> PROCESS FOR BONDING FIBROUS WEB  <b>(57) Abstract</b>  A process for forming a fibrous web in the presence of a water-absorbent material, such as a superabsorbent, in which a web of non-water-absorbent fibers and water-absorbent materials is formed and then contacted with an aqueous solution of a binder such as latex in an amount of 5 wt.%, or an uncured binder.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Process for Bonding Fibrous Web

The present invention relates to a process for bonding a fibrous web which includes water-absorbent material such as water-absorbent fibers. In particular the present invention relates to bonding a fibrous web containing so-called superabsorbent fibers.

5 The invention also relates to an article of manufacture comprising a fibrous web made in accordance with the process.

Fibrous webs containing water-absorbent compositions are widely used in the manufacture of products which require high absorption capability; for example, surgical and dental sponges, tampons, sanitary napkins and pads, bandages, disposable  
10 diapers, meat trays, filters, spill control materials, waste management materials, cable wrap, protective articles such as operating gowns and household pet litter. Fibrous webs containing water-absorbent compositions are also used in the modification of soil to improve water-retention and increase air capacity and in a host of other applications.

15 Water-absorbent compositions suitable for use in these fibrous webs may be in any suitable form including powders, fibers and filaments, with fibers being particularly preferred.

As used herein, the term "water" when used in the phrases "water-absorbing", "water-absorbent" and "water-swellaable" is understood to mean not only water but also  
20 aqueous media such as electrolyte solutions, such as body fluids.

The fibrous webs of the type with which the present invention is concerned are generally formed from non-water-absorbent fibers. By "non-water-absorbent" we mean that the fibers do not absorb water to an appreciable extent. Suitable materials from which these fibers may be formed include natural materials such as wood pulp  
25 or cellulose or synthetic materials such as synthetic cellulose, viscose, polyester, non-water-absorbent polymers of ethylene, non-water-absorbent polymers of propylene, polyamide and ethylene-propylene copolymer fibers, and mixtures thereof with

polyester, polyethylene and polypropylene fibers being particularly preferred. Particularly preferred fibers are those selected from the group consisting of rayon fibers, cellulose ester fibers, protein fibers, polyamide fibers, polyester fibers, polyvinyl fibers, polyolefin fibers, polyurethane fibers, aramid fibers, glass fibers and mixtures thereof. In one alternative, the non-water-absorbent fibers may be, or may  
5 fibers having hollow cores such as the polyester, typically polyethylene terephthalate fibers commercially available from E.I. DuPont de Nemours under the trade mark HOLLOWFILL.

The fibrous web additionally includes water-absorbent compositions, which are  
10 preferably water-absorbent fibers.

A number of water-absorbent compositions have been developed which exhibit the capacity to be water-absorbing. For example, U.S. Patent numbers 3,954,721 and 3,983,095 disclose preparations for derivatives of copolymers of maleic anhydride with at least one vinyl monomer in fibrous form. The fibrous copolymers are rendered  
15 hydrophillic and water-swellaable by reaction with ammonia or an alkali metal hydroxide. U.S. Patent No. 3,810,468 discloses lightly cross-linked olefin-maleic anhydride copolymers prepared as substantially linear copolymers and then reacted with a diol or a diamine to introduce cross-linking. The resultant lightly cross-linked copolymers are treated with ammonia or an aqueous or alcohol solution of an alkali  
20 metal hydroxide. U.S. Patent No. 3,980,663 describes water-swellaable absorbent articles made from carboxylic polyelectrolytes via cross-linking with glycerine diglycidyl ether. These patents are incorporated herein by reference.

European Published Application No. 0 268 498 (incorporated herein by reference) describes a water-absorbent composition formed by causing a substantially linear  
25 polymer of water-soluble ethylenically unsaturated monomer blends comprising carboxylic and hydroxylic monomers to cross-link internally.

Further examples of water-absorbent compositions are those produced from a copolymer of an  $\alpha,\beta$  unsaturated monomer having at least one pendant unit selected

from a carboxylic acid group and derivatives thereof and a copolymerisable monomer. A proportion of the pendant units are present in the final copolymer as the free acid and a proportion as the salt of the acid. These copolymers are capable of being cross-linked, either internally or with a variety of cross-linking agents, to form the water-swella-  
5 ble composition. Examples of water-swella-ble compositions of this type can be found in U.S. Patent Nos 4,616,063, 4,705,773, 4,731,067, 4,743,244, 4,788,237, 4,813,945, 4,880,868 and 4,892,533 and European Patent Nos 0 272 074 and 0 264 208 and European Published Application No. 0 436 514 which are incorporated herein by reference.

10 Derivatives of carboxylic acid groups include carboxylic acid salt groups, carboxylic acid amide groups, carboxylic acid imide groups, carboxylic acid anhydride groups and carboxylic acid ester groups.

Other examples of water-absorbent compositions can be found in European Published Application Nos 0 269 393, 0 342 919 and 0 397 410, British Patent Application  
15 Nos 2 082 614 and 2 126 591, U.S. Patent Nos 4,418,163, 4,418,163 3,989,586, 4,332,917, 4,338,417, 4,420,588 and 4,155,957 and French Patent Application No. 2 525 121 which are incorporated herein by reference.

The fibrous web may be formed as a non-woven web by any conventional means. Suitable means include air-laying, wet-laying and carding. The fibers are then  
20 bonded, for example by the action of an adhesive and/or heat. However, aqueous solutions of adhesives have not generally been utilised when the web contains water-absorbent compositions as it is believed that the water in the aqueous solution will be absorbed by the water-absorbent compositions which, having been activated, will not function satisfactorily in use. Additionally or alternatively, the aqueous solution of  
25 the adhesive may coat the water-absorbent composition, rendering it ineffective.

In EP 0 357 474 an aqueous adhesive solution is used to bond the fibers in the web. However, such bonding takes place before the water-absorbent material is introduced into the web. In particular, an air-laid web of non-water-absorbent fibers is first

sprayed on one side with a latex binder before being passed through an oven where the latex binder is at least partially cured. The web is then sprayed with precursors of the water-absorbing composition onto the side of the web remote from that on which the latex was sprayed. The web is then passed through a dryer where cross-  
5 linking occurs to form the superabsorbent *in situ*.

In US 5128082 and US 5378528 the aqueous binder is applied to a fibrous web which incorporates a superabsorbent material. As in EP 0357474 the binder, which is preferably latex, is cured to bind the fibrous web. The amount of latex used is in the range of 5 to 30 weight percent of the final structure, and preferably from about 10  
10 to 20 weight percent.

The use of an aqueous solution of an adhesive such as latex is also described in WO 90/11184. Here, an aqueous solution of a binder is used to bind water-absorbent particles to the fibers of the web. The particles of the superabsorbent are preferably added after the fibers have been wetted by the binder such that the binder does not  
15 coat the particles and thereby interfere with their absorbency.

The known processes which involve the use of aqueous binders have certain disadvantageous and drawbacks. In particular, the binder, whether applied before or after the inclusion of the superabsorbent composition into the web, reduces the absorbency of the resultant web. In addition, the process in which the binder is  
20 applied before the web is sprayed with the precursors of the water-absorbing polymer is unsuitable where it is desired that the superabsorbent is to be in the form of fibers.

We have now discovered the aforementioned problems may be reduced or obviated if the binder used to bind the fibers of the fibrous web is used in an amount of less than 5 weight percent of the structure being formed. This is particularly suitable where the  
25 web includes the water-absorbent material in fibrous form. Surprisingly, this reduced amount of binder is sufficient to bind the web. One benefit of using this reduced amount of binder is that the absorbency of the web formed is higher than has been previously achieved using aqueous binders in accordance with known techniques.

Thus, according to a first aspect of the present invention there is provided a process for bonding a fibrous web in the presence of water-absorbent material wherein the pre-formed web is contacted with an aqueous solution of a binder, the binder being used in an amount of less than 5 weight percent of the fibrous web.

5     Suitable binders include cationic starch, polyvinyl alcohol, pearl starch, natural gums, such as tragacanth, karaya and guar, vinyl acetate-acrylic acid copolymers, polyvinyl chlorides, polyvinyl acetates, ethylene-vinyl acetates, styrenebutadiene carboxylates, natural latex, synthetic latex, including polyacrylates such as polyethylacrylate and copolymers thereof, polyacrylonitriles and thermosetting cationic resins such as urea  
10     formaldehyde resins and polyamide-epichlorhydrin resins, with natural or synthetic latex being preferred. Examples of commercially available compositions which are suitable binders include AIRBOND, AIRFLEX and VINAC of Air Products Inc., HYCAR and GEON of Goodrich Chemical Co., and FULATEX of HB Fuller Company.

15     The binder may be applied to the web by any suitable means. In one arrangement, the web may be immersed in the binder; excess binder can then be removed by, for example, applying pressure to the web. In one alternative arrangement, the binder is sprayed onto the web. The binder may be sprayed onto one or both sides of the web. Spray bonding is the generally preferred means of applying the binder to the web. It  
20     is particularly preferred in applications where the retention of the bulk or loft of the web is important. The binder may be sprayed onto the fibrous web to obtain spot welds at the points where fibers are in mutual contact. The binder is preferably used in an amount of from 1wt % to 5wt %, more preferably 2wt % to 4wt %. Amounts of less than 1wt % may also be used.

25     The treated web is then allowed to cure. Curing is preferably achieved by passing the web that has been treated with the aqueous solution of the binder through an oven. During curing, cross-linking of the binder will occur and binding will thereby be effected. In order to effect cross-linking the binder will contain an amount of a suitable cross-linking agent. One suitable cross-linking agent is N-methylol

acrylamide.

The binder may include suitable additives such as defoamers, surfactants, external crosslinkers, thickeners, flame retardants, catalysts, pH adjusters, dyes and pigments, fillers, optical brighteners, sewing aids and water repellents.

5 We have also discovered an improved process for forming a fibrous web in the presence of water-absorbent material wherein the binder is allowed to dry but does not cure to an appreciable extent. This process also overcomes many of the aforementioned problems.

10 Thus, according to the second aspect of the present invention there is provided a process for forming a fibrous web in the presence of water-absorbent material wherein the binder being free of cross-linker is applied to the fibrous web and allowed to dry.

Any suitable binder may be used provided that it is capable of being provided in aqueous form and of hardening on removal of the water. The binders listed in connection with the above-first aspect of the invention are particularly suitable  
15 provided that they do not include a cross-linking agent.

A preferred binder is an aqueous solution of the uncured polymer from which water-absorbent compositions may be formed. A particularly suitable binder is an aqueous solution of the uncured polymer from which the water-absorbent composition present in the web is formed.

20 We have found that a particularly suitable binder is a composition comprising a copolymer having pendant carboxylic acid groups or other groups convertible to carboxylic acid groups, wherein at least a portion of the carboxylic acid groups are partially neutralised. The copolymer may be formed from an  $\alpha,\beta$ -unsaturated monomer having at least one pendant unit selected from a carboxylic acid group and  
25 derivatives thereof and a copolymerisable monomer.



The use of the uncured polymer from which the water-absorbent composition is formed as a binder results in a web having improved absorbency. Further, as the polymer of the binder is one from which the water-absorbent composition may be formed, the binder will be compatible with the water-absorbent composition and will not have a deleterious effect thereon.

The binder formed from the polymer from which a water-absorbent composition may be formed may undergo some crosslinking on drying and fall within the definition of the second aspect of the present invention. If cross-linking occurs, enhanced absorbency of the web will be achieved. Crosslinking may be internal cross-linking or, alternatively, the binder solution may contain some external cross-linking agents. Suitable cross-linking agents include: monomers containing at least two hydroxyl groups such as alkylene glycols containing 2-10 carbon atoms and their ethers, cycloalkylene glycols, Bisphenol A, hydroxy alkylene derivatives of Bisphenol A, hydroquinone, phloroglucinol, hydroxy alkylene derivatives of diphenols, glycerol, erythritol, pentaerythritol, and mono-, di, or oligo-saccharides; heterocyclic carbonates; and monomers containing at least one amine group and at least one hydroxyl group such as ethanolamine, tris (hydroxymethyl) aminomethane, 3-amino-1-propanol, DL-1-amino-2-propanol, 2-amino-1-butanol, N,N-dimethylethanolamine, diisopropanol-amine methyl diethanol amine, triethanol amine, 2-(methylamino)ethanol and the like.


Particularly suitable uncured, in the sense of the invention, copolymers for use as a binder in the present invention contain from about 25 to about 75 mole percent recurring units of the  $\alpha,\beta$ -unsaturated monomer and from about 75 to about 25 mole percent recurring units of a copolymerisable monomer. The copolymer preferably contains from about 35 to about 65 mole percent of recurring units of at least one  $\alpha,\beta$ -unsaturated monomer and from about 65 to about 35 mole percent of at least one copolymerisable co-monomer. Most preferably, the copolymer will be an equimolar copolymer.

Suitable  $\alpha,\beta$ -unsaturated monomers are those bearing at least one pendant carboxylic

acid unit or derivative of a carboxylic acid unit. Derivatives of carboxylic acid units include carboxylic acid salt groups, carboxylic acid amide groups, carboxylic acid imide groups, carboxylic acid anhydride groups and carboxylic acid ester groups.

5 Examples of suitable  $\alpha,\beta$ -unsaturated monomers include maleic acid, crotonic acid, fumaric acid, mesaconic acid, the sodium salt of maleic acid, the sodium salt of 2-methyl, 2-butene dicarboxylic acid, the sodium salt of itaconic acid, maleamic acid, maleamide, N-phenyl maleimide, maleimide, maleic anhydride, fumaric anhydride, itaconic anhydride, citraconic anhydride, ethyl maleic anhydride, diethylmaleate, methylmaleate and the like and mixtures thereof.

10 Any suitable copolymerisable co-monomer can be employed. Examples of suitable co-monomers include ethylene, propylene, isobutylene,  $C_1$  to  $C_4$  alkyl methacrylates, vinyl acetates, methyl vinyl ether, isobutyl vinyl ether and styrenic compounds having the formula:



15 wherein R represents hydrogen or an alkyl group having from 1 to 6 carbon atoms, and wherein the benzene ring is substituted or unsubstituted.

Suitable alkyl acrylates include methyl acrylate, ethyl acrylate, isopropyl acrylate, n-propyl acrylate, n-butyl acrylate, and the like and mixtures thereof.

Suitable alkyl methacrylates include methyl methacrylate, ethyl methacrylate, isopropyl

methacrylate, n-propylmethacrylate, n-butyl methacrylate, and the like and mixtures thereof.

One alternative uncured polymer is formed from a water-soluble blend of monoethylenically unsaturated monomers. the polymer may include a comonomer.

5 The polymer preferably comprises 50 to 95% by weight of an ethylenically unsaturated monomer and 5 to 50% by weight of a copolymerisable ethylenically unsaturated monomer.

Preferred carboxylic monomers include methacrylic acid, acrylic acid, maleic acid or anhydride, itaconic acid and ethylenically unsaturated carboxylic acids or anhydrides.

10 Some of the carboxylic monomer units in the copolymer may be replaced by monomer units derived from an ethylenically unsaturated sulphonic acid such as 2-acrylamido-2-methylpropane sulphonic acid or allyl sulphonic acid.

The or each copolymerisable ethylenically unsaturated monomer may be selected from a water-soluble ethylenically unsaturated monomer such as acrylamide or a water-insoluble monomer, for example an olefin, such as isobutylene, an aromatic ethylenically unsaturated monomer, such as styrene or a substituted styrene, an alkyl ester of acrylic or methacrylic acid, such as methyl or ethyl acrylate or methacrylate, butyl acrylate or methacrylate or 2-ethylhexyl acrylate or methacrylate, vinyl acetate or acrylonitrile. Other monomers that may be used include ethylenically unsaturated monomers that carry a pendent group of the formula  $-A_mB_nA_pR$  where B is ethyleneoxy, n is a integer of at least 2, A is propyleneoxy or butyleneoxy, m and p are each an integer less than n and preferably below 2 and most preferably zero, and R is a hydrophobic group containing at least 8 carbon atoms as described in more detail in EP-A-213799. The comonomers(s) are generally present in amounts of at least 5% and preferably at least 10% by weight based on the monomers used for forming the copolymer, and they may be present in amounts up to about 50%, generally below 45%, by weight.

15  
20  
25

The fibrous web produced in accordance with the above-mentioned first or second

aspect of the invention is suitable for use in the production of articles of manufacture.

Thus, in accordance with a third aspect of the present invention, there is provided an article of manufacture comprising a fibrous web made in accordance with the process of the above first or second aspect.

5 The article of manufacture is preferably selected from the group consisting of:  
disposable diapers; sanitary napkins; tampons; pant liners; adult incontinence pads;  
coverstock for feminine hygiene products; surgical and dental sponges; bandages;  
patient underpads; wipes; domestic wipes; industrial wipes; packaging; medical tray  
10 pads; fenestration drapes; filters; spill control materials; waste management materials;  
protective articles; operating gowns; mortuary pads; cable wrap; food tray pads; food  
preservation articles; seed germination pads; household pet litter; roofing materials;  
automotive trim; furniture; bedding; clothing; and soil modifiers.

Where the article of manufacture comprises a fibrous web made in accordance with  
the process of the above second aspect of the invention, the binder is sufficient to  
15 retain the integrity of the web during use but is sufficiently degradable in the presence  
of a large volume of water, particularly turbulent water such as is found in a toilet,  
that the article is particularly suitable for disposal in water, such as in a toilet.

Preferred embodiments of the present invention will now be described with reference  
to the accompanying drawing in which:

20 Figure 1 is a schematic flow diagram outlining the  
process of the present invention.

In the following examples, the non-water-absorbent fibers and the superabsorbent  
fibers are fed to formers 1 and 2. In the pilot plant, a Laroche 400 fiber feed was  
employed to feed fibers to the formers. The fibers are fed from the formers onto a  
25 belt 3 comprising the forming table. The fibers are held in place by the action of  
vacuum boxes 4. Two light compactor rolls 5 are used to densify and compact the

web.

5 The aqueous solution of the binder (latex) optionally containing a cross-linking agent was sprayed onto one side of the web. The spray system 6 is located between the end of the forming table 3 and the dryer 7. In an alternative arrangement a second spray system and dryer (not shown) may be located after the dryer 7. This second spray system may spray the binder onto the side of the web opposite to that sprayed on the first side.

10 The binder may contain a cross-linking agent or may be free of cross-linker. As the web passes through the dryer 7. The dryer, which is preferably an air dryer, causes the water to evaporate. Where the binder includes a cross-linker, the binder will cure and thereby strengthens. Where the binder is free of cross-linker, the binder dries as it passes through the dryer and thereby strengthens. In addition, where the non-water-absorbent fibers of the web are thermal bonding fibers, the dryer 7 activates these fibers. A compactor roll 8 may be located within the dryer.

15 Calendaring rolls 9 may be located after the dryer. These rolls may be used to emboss the web, reduce calliper or modify the surface of the web.

The final bound web preferably has a density of from 0.05 to 0.2 gcm<sup>-1</sup>

#### Examples 1-6

20 Using the above-described process, fibrous webs of the compositions set out in Table 1 were provided.

Table 1

Run No	Fluff (wt%)	Superabsorbent Fiber (wt%)	Latex (wt%)	Basis weight (g/m <sup>2</sup> )
1	71	25	4	124
2	76	20	4	102
3	76	20	4	155
4	60	36	4	154
5	66	30	4	131
6	100	0	4	120

By 'fluff', we mean all components of the web other than the superabsorbents and latex.

The absorbency of the webs produced in Examples 1 to 6 were tested in accordance with the following test procedure:

A 10 x 30 cm strip of the sample was cut from the absorbent material to be tested. Approximately 2 cm of the specimen was immersed into 0.9% saline and the weight increase due to absorption was measured after 30 minutes. The results of the tests are set out in Table 2

Table 2

Run No	Absorption (g)
1	24
2	23
3	36
4	44
5	27
6	16

Comparative Test

Thus it will be understood that even though an aqueous solution of a binder is used to bind the web, the water-absorbent composition functions to enhance the absorbency of the web.

CLAIMS:

1. A process for bonding a fibrous web in the presence of water-absorbent material wherein a pre-formed web is contacted with an aqueous solution of a binder, the binder solution containing a cross-linking agent, the binder  
5 being present in an amount of less than 5 weight percent of the fibrous web.
2. A process according to Claim 1 wherein the binder is selected from the group consisting of cationic starch, polyvinyl alcohol, pearl starch, natural gums, such as tragacanth, karaya and guar, vinyl acetate-acrylic acid copolymers, polyvinyl chlorides, polyvinyl acetates, ethylene-vinyl acetates,  
10 styrenebutadiene carboxylates, natural latex, synthetic latex, including polyacrylates such as polyethylacrylate and copolymers thereof, polyacrylonitriles or thermosetting cationic resins such as urea formaldehyde resins and polyamide-epichlorhydrin resins.
3. A process according to Claim 1 wherein the binder is natural or synthetic  
15 latex.
4. A process according to Claim 1 wherein the binder is applied to the fibrous web by spraying.
5. A process according to Claim 1 wherein the binder is natural or synthetic latex and is applied to the fibrous web by spraying.
- 20 6. An article of manufacture comprising a fibrous web made in accordance with the process of Claim 1.
7. An article of manufacture according to Claim 6 wherein said binder is natural or synthetic latex.



8. An article of manufacture according to Claim 7 wherein the article is selected from the group consisting of: disposable diapers; sanitary napkins; tampons; pant liners; adult incontinence pads; coverstock for feminine hygiene products; surgical and dental sponges; bandages; patient underpads; wipes; domestic wipes; industrial wipes; packaging; filters; medical tray pads; fenestration drapes; mortuary pads; cable wrap; food tray pads; food preservation articles; seed germination pads; household pet litter; roofing materials; automotive trim; furniture; bedding; clothing; and soil modifiers.
9. A process for forming a fibrous web in the presence of water-absorbent material wherein the binder, which is substantially free of cross-linker is applied to the fibrous web and allowed to dry.
10. A process according to Claim 9 wherein the binder is selected from the group consisting of cationic starch, polyvinyl alcohol, pearl starch, natural gums, such as tragacanth, karaya and guar, vinyl acetate-acrylic acid copolymers, polyvinyl chlorides, polyvinyl acetates, ethylene-vinyl acetates, styrenebutadiene carboxylates, natural latex, synthetic latex, including polyacrylates such as polyethylacrylate and copolymers thereof, polyacrylonitriles or thermosetting cationic resins such as urea formaldehyde resins and polyamide-epichlorhydrin resins.
11. A process according to Claim 9 wherein the binder is natural or synthetic latex.
12. A process according to Claim 9 wherein the binder is an aqueous solution of the uncured polymer from which a water-absorbent composition may be formed.
13. A process according to Claim 12 wherein the binder is an aqueous solution of the uncured polymer from which the water-absorbent composition present in the web is formed.


14. A process according to Claim 13 wherein the binder is an aqueous solution of an uncured copolymer comprising from about 25 to about 75 mole percent recurring units of at least one  $\alpha,\beta$ -unsaturated monomer bearing at least one pendant unit selected from the group consisting of carboxylic acid units and derivatives of carboxylic acid units, and from about 75 to about 25 mole percent recurring units of at least one copolymerisable comonomer.
15. A process according to Claim 9 wherein the binder is applied to the fibrous web by spraying.
16. A process according to Claim 9 wherein the binder is natural or synthetic latex and is applied to the fibrous web by spraying.
17. An article of manufacture comprising a fibrous web made in accordance with the process of Claim 9.
18. An article of manufacture according to Claim 17 wherein said binder is natural or synthetic latex.
19. An article of manufacture according to Claim 18 wherein the article is selected from the group consisting of: disposable diapers; sanitary napkins; tampons; pant liners; adult incontinence pads; coverstock for feminine hygiene products; surgical and dental sponges; bandages; patient underpads; wipes; domestic wipes; industrial wipes; filters; spill control materials; waste management materials; protective articles; operating gowns; packaging; medical tray pads; fenestration drapes; mortuary pads; cable wrap; food tray pads; food preservation articles; seed germination pads; household pet litter; roofing materials; automotive trim; furniture; bedding; clothing; and soil modifiers.
20. An article of manufacture according to Claim 17 wherein said binder is an aqueous solution of an uncured copolymer comprising from about 25 to

about 75 mole percent recurring units of at least one  $\alpha,\beta$ -unsaturated monomer bearing at least one pendant unit selected from the group consisting of carboxylic acid units and derivatives of carboxylic acid units, and from about 75 to about 25 mole percent recurring units of at least one copolymerisable comonomer.

21. An article of manufacture according to Claim 20 wherein the article is selected from the group consisting of: disposable diapers; sanitary napkins; tampons; pant liners; adult incontinence pads; coverstock for feminine hygiene products; surgical and dental sponges; bandages; patient underpads; wipes; domestic wipes; industrial wipes; spill control materials; waste management materials; protective articles such as operating gowns and packaging; filters; medical tray pads; fenestration drapes; mortuary pads; cable wrap; food tray pads; food preservation articles; seed germination pads; household pet litter; roofing materials; automotive trim; furniture; bedding; clothing; and soil modifiers.

1/1

Fig.1.



# INTERNATIONAL SEARCH REPORT

Internat. Application No.  
PCT/EP 97/00376

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 D04H1/64 D06M15/19 D06M15/37 D06M15/59 D06M15/693  
D21H17/20

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 D04H D06M D21H A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR 2 679 573 A (PERFOJET SA) 29 January 1993 see page 4, line 1-9 see page 4, line 28 - page 6, line 27	9,10,12, 15,17,19
Y	---	1-21
Y	WO 96 37650 A (CAMELOT SUPERABSORBENTS LTD ;CAMELOT SUPERABSORBENTS BV (NL); DING) 28 November 1996 see the whole document	1-21
A	---	1-21
A	WO 92 09660 A (UNION OIL CO) 11 June 1992 see page 25, line 7 - line 23	1-21
A	---	1-21
	EP 0 608 460 A (LION CORP) 3 August 1994 see claims; example 3 ---	1-21
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

\*&\* document member of the same patent family

Date of the actual completion of the international search

25 September 1997

Date of mailing of the international search report

06.11.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+ 31-70) 340-3016

Authorized officer

Barathe, R

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 97/00376

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 003 186 A (AIR PROD & CHEM) 25 July 1979 see page 3, line 21 - page 4, line 15 ---	1-21
A	EP 0 357 474 A (JAMES RIVER CORP) 7 March 1990 cited in the application see the whole document ---	1-21
A	US 5 378 528 A (MAKOUJI KAMBIZ B) 3 January 1995 cited in the application see the whole document -----	1-21

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Internal Application No

PCT/EP 97/00376

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 2679573 A	29-01-93	DE 69204403 D DE 69204403 T EP 0530113 A JP 5209349 A US 5393304 A US 5295997 A	05-10-95 01-02-96 03-03-93 20-08-93 28-02-95 22-03-94
WO 9637650 A	28-11-96	AU 6000596 A	11-12-96
WO 9209660 A	11-06-92	AU 1238292 A	25-06-92
EP 0608460 A	03-08-94	NONE	
EP 0003186 A	25-07-79	US 4245744 A US 4258849 A CA 1104026 A JP 54104962 A US 4343403 A US 4343133 A CA 1109758 A JP 54104963 A US 4372447 A US 4343134 A	20-01-81 31-03-81 30-06-81 17-08-79 10-08-82 10-08-82 29-09-81 17-08-79 08-02-83 10-08-82
EP 0357474 A	07-03-90	US 5071681 A	10-12-91
US 5378528 A	03-01-95	US 5128082 A EP 0463716 A	07-07-92 02-01-92